Test Report

Report No. A2250403889101003 Page 1 of 4

Company Name JKOO INDUSTRY CO., LTD.

Address #249-251 JIANCHUAN RD., LONGQUAN, ZHEJIANG, CHINA

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

Sample Name	sample #3
Type	60
Material	spring steel
Sample Received Date	Jun. 11, 2025
Testing Period	Jun. 11, 2025-Jun. 18, 2025

Test Requested

No.	Test Item
1	Element analysis

Test Result(s): Please refer to the following pages.

Approved by Andrew Wang
Approved Signatory

Date Jun. 18, 2025

Centre Testing International Pinbiao (Shanghai) Co., Ltd.

No.RBAF56CA34
No.1351, Wanfang Road, Minhang District, Shanghai, China.

Test Report

Tested Sample(s)

Sample No.	Sample Name	Type	Material
A2250403889101003	sample #3	60	spring steel

Sample Photo(s)

A2250403889101003

Test Report

Test Item: Element analysis

1. Test Equipment:

Equipment Name	Model
Direct-reading Spectrometer	SPECTROMAXx

2. Environmental Conditions： Temperature：24.0℃； Humidity：59.0%RH

3. Test Standard: ASTM E415-17

4. Test Result(s)

Item	Result,%
C	0.59
Si	1.65
Mn	0.84
P	0.019
S	0.003
Cr	0.23
Ni	0.01
Mo	<0.01
Cu	0.02
V	<0.01

Note: The testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.

Test Report

Remark: The testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.

Statement:

1.This report is considered invalid without approved signature, special seal and the seal on the perforation;

2.The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which CTI hasn't verified;

3.The result(s) shown in this report refer(s) only to the sample(s) tested;

4.Without written approval of CTI, this report can't be reproduced except in full;

5.In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.

*** End of Report ***